

# TIMETAL<sup>®</sup> 75A

## COMMERCIALLY PURE TITANIUM

TIMETAL 75A is equivalent to ASTM Grade 4. It has the highest strength of the four ASTM commercially pure titanium grades in addition to good ductility and moderate formability. The benefits of the good strength to weight ratio of TIMETAL 75A are retained at moderate temperatures.

TIMETAL 75A is typically used in continuous service up to 800°F (425°C) and in intermittent service up to 1000°F (540°C). It also has good impact properties at low temperatures. In addition, TIMETAL 75A can be satisfactorily welded, machined, cold worked, hot worked, and cast.

TABLE 1

### CHEMICAL COMPOSITION

ELEMENT	WEIGHT %
	<i>Maximum</i>
Oxygen	0.40
Nitrogen	0.05
Carbon	0.08
Iron	0.50
Hydrogen*	0.015
Residual Elements, each	0.10
Residual Elements, total	0.40
Titanium	Remainder

\* Hydrogen content depends on product form.

TABLE 2

### PHYSICAL PROPERTIES

PROPERTY	VALUE	
	<i>English</i>	<i>SI</i>
Density	0.163 lb in <sup>-3</sup>	4.51 g cm <sup>-3</sup>
Beta Transus	1740°F	950°C
Thermal Conductivity	9.80 Btu hr <sup>-1</sup> ft <sup>-1</sup> °F <sup>-1</sup>	16.95 W m <sup>-1</sup> K <sup>-1</sup>
Electrical Resistivity	24 μΩ•in	0.60 μΩ•m
Magnetic Permeability	Nonmagnetic	
Mean Coefficient of Thermal Expansion		
68-212°F (20-100°C)	4.8 x 10 <sup>-6</sup> in in <sup>-1</sup> °F <sup>-1</sup>	8.6 x 10 <sup>-6</sup> m m <sup>-1</sup> °C <sup>-1</sup>
68-572°F (20-300°C)	5.3 x 10 <sup>-6</sup> in in <sup>-1</sup> °F <sup>-1</sup>	9.5 x 10 <sup>-6</sup> m m <sup>-1</sup> °C <sup>-1</sup>
68-932°F (20-500°C)	5.4 x 10 <sup>-6</sup> in in <sup>-1</sup> °F <sup>-1</sup>	9.7 x 10 <sup>-6</sup> m m <sup>-1</sup> °C <sup>-1</sup>
Elastic Modulus*	15.2-17.4 Msi	105-120 GPa

\* Typical values at room temperature of about 68-78°F (20-25°C)

TABLE 3

### HEAT TREATMENT

<i>Anneal</i>	<i>Stress Relieve</i>
1292°F (700°C) 1 hour / Air Cool	932°F (500°C) 30 mins / Air Cool

TABLE 4

### TYPICAL MECHANICAL PROPERTIES

<i>UTS</i> <i>ksi (MPa)</i>	<i>0.2% YS</i> <i>ksi (MPa)</i>	<i>Elongation</i> <i>%</i>	<i>Reduction in Area</i> <i>%</i>	<i>Bend</i> <i>Radius</i>
99 (680)	81 (560)	23	46	3.0T



TABLE 5

FATIGUE AND TENSILE PROPERTIES

ROTATING BEND

Condition	Ultimate Tensile Strength ksi (MPa)	Fatigue Limit 10 <sup>7</sup> Cycles ksi (MPa)	Fatigue Ratio
Smooth, K <sub>t</sub> = 1	98 (674)	±55 (376)	0.56

TABLE 6

TYPICAL ELEVATED TEMPERATURE TENSILE PROPERTIES

Test Temperature	0.2% Yield Strength ksi (MPa)	Ultimate Tensile Strength ksi (MPa)	Elongation %
212°F (100°C)	53 (364)	79 (537)	27
392°F (200°C)	33 (231)	55 (381)	33
572°F (300°C)	22 (149)	41 (284)	35
752°F (400°C)	15 (101)	33 (227)	33
842°F (450°C)	13 (92)	30 (209)	—

The data and other information contained herein are derived from a variety of sources which TIMET believes are reliable. Because it is not possible to anticipate specific uses and operating conditions, TIMET urges you to consult with our technical service personnel on your particular applications.

For more information, please contact the TIMET Sales Office/Service Center nearest you, TIMET's Technical Laboratories or TIMET's Website @ [www.timet.com](http://www.timet.com)

NORTH AMERICA

Hartford, CT	860-627-7051
Toronto, OH	740-537-5600
St. Louis, MO	800-753-1550
Dallas, TX	817-329-5035
Tustin, CA	714-573-1000

EUROPE

Birmingham, England	44-121-356-1155
Paris, France	33-4-79-89-73-73
Düsseldorf, Germany	49-211-230-880

TECHNICAL SUPPORT

Henderson, NV	702-566-4416
Birmingham, England	44-121-332-5381



First in Titanium Worldwide

